

CLAIMS

1. A semiconductor component (30) having a silicon-bearing layer (32) and a praseodymium oxide layer (40), characterized in that arranged between the silicon-bearing layer (32) and the praseodymium oxide layer (40) is a mixed oxide layer (34) containing silicon, praseodymium and oxygen, which is of a layer thickness of less than 5 nanometers.
2. A semiconductor component as set forth in claim 1 wherein the mixed oxide layer (34) is of a layer thickness of a maximum of 3 nanometers.
3. A semiconductor component as set forth in one of the preceding claims wherein the mixed oxide (34) is a pseudo-binary, non-stoichiometric silicate or an alloy of the type $(\text{Pr}_2\text{O}_3)_x(\text{SiO}_2)_{1-x}$.
4. A semiconductor component as set forth in claim 3 wherein x increases between the silicon-bearing layer (32) and the praseodymium oxide layer (40).
5. A semiconductor component as set forth in one of the preceding claims wherein the silicon-bearing layer (32) comprises doped or undoped silicon-germanium.
6. A semiconductor component as set forth in one of claims 1 through 4 wherein the silicon-bearing layer comprises doped or undoped silicon.
7. A semiconductor component 30 as set forth in claim 5 or claim 6 wherein the silicon-germanium layer or the silicon layer has an (001) orientation at the interface to the mixed oxide layer.
8. An MOSFET as set forth in one of the preceding claims.

9. A memory cell as set forth in one of claims 1 through 7.
10. A production process for an electronic component with a step of depositing a praseodymium oxide layer (40) on a silicon-bearing layer (32),
characterized in that prior to said deposit step a step of depositing a mixed oxide layer (34) containing silicon, praseodymium and oxygen is effected at a substrate temperature of less than 700°C.
11. A process as set forth in claim 10 wherein the steps of depositing a mixed oxide layer (34) and depositing a praseodymium oxide layer (40) are effected in the form of deposition out of the gaseous phase.
12. A process as set forth in claim 11 wherein the deposit steps are effected by means of molecular beam deposition.
13. A process as set forth in claim 11 wherein the deposit steps are effected by means of chemical vapor phase deposition.
14. A process as set forth in one of claims 10 through 13 wherein the step of depositing the mixed oxide layer (34) is effected in an oxygen-bearing gas atmosphere.
15. A process as set forth in one of claims 10 through 14 wherein the step of depositing the praseodymium oxide layer (40) is effected in an oxygen-bearing gas atmosphere.
16. A process as set forth in one of claims 10 through 15 wherein the step of depositing the mixed oxide layer (34) is effected by means of a starting material which contains or consists of praseodymium oxide in the form Pr_6O_{11} .
17. A process as set forth in one of claims 10 through 16 wherein the step of depositing the praseodymium oxide layer (40) is effected by

means of a starting material containing praseodymium oxide in the form Pr_6O_{11} .

18. A process as set forth in one of claims 10 through 17 wherein the step of depositing the mixed oxide layer (34) is effected at a temperature of a maximum of 680°C .

19. A process as set forth in one of claims 12 through 17 wherein the step of depositing the mixed oxide layer (34) is effected at a temperature of between 600°C and 650°C .